

LABORATORY TEST REPORT

ULR - TC587519000001201F

Form / Format No : 32

Page 1 of 2


Issued To: Bhagwati Tirath Polycontainers Industries P. Ltd. Survey No. 260/3/1, Demni Road, Village Dadra, U.T. of Dadra & Nagar Haveli – 396 193. Kind Attn : --	Test Report No	100/10-1920/4610
	Date	23 Oct 2019
	Date of Start of Test	08 Oct 2019
	Date of Completion of Test	23 Oct 2019
	Customer Ref.No	BTPIPL/IIOP/01/2019-20
	Ref. Date	07 Oct 2019
	Sampling Plan	Sampling done by the party
Sample Description : Two set of sample said to be "Plastic container with lid" marked as below.		

Test Results

Sr No.	Test	Unit	Results Obtained	Tested as per
1			Rectangle box	
1 . 1	Overall Migration (Extraction value) with distilled water at 40°C for 10 days	mg/L	5.8 (no colour migration was observed)	IS 9845 - 1998 RA 2015
1 . 2	Overall Migration (Extraction value) with n-heptane at 38°C for 30 min	mg/L	0.47 (no colour migration was observed)	IS 9845 - 1998 RA 2015
2			Round box	
2 . 1	Overall Migration (Extraction value) with distilled water at 40°C for 10 days	mg/L	4.4 (no colour migration was observed)	IS 9845 - 1998 RA 2015

TESTED BY 46


ASST./DY./JT. DIRECTOR


HEAD
LABORATORIES DIVISION

This report is for Private use only Not to be used for Publicity or Litigation

Testing laboratories of Mumbai are certified by ISO 9001: 2015, NABL, BIS, Directorate General of Shipping and Directorate General of Civil Aviation, Govt. of India for specified tests.

Head Office: Plot E-2, Road No. 8, MIDC, Area, Andheri (East), Mumbai 400093.

Tel: +91-22-2821 9803 / 6751 / 9469, 28391506, 28329623, 28254631, Fax: +91-22-28328178 / 28375302 Email : rdiip@iip-in.com, Website: www.iip-in.com



भारतीय पैकेजिंग संस्थान Indian Institute of Packaging

An autonomous body under the Ministry of Commerce & Industry, Govt. of India

LABORATORY TEST REPORT

Test Report No. : 100/10-1920/4610

ULR - TC587519000001201F

Form / Format No : 32

Date : 23 Oct 2019

Page 2 of 2

Sr No.	Test	Unit	Results Obtained	Tested as per
2.2	Overall Migration (Extraction value) with n-heptane at 38°C for 30 min	mg/L	1.11 (no colour migration was observed)	IS 9845 - 1998 RA 2015

General Remarks

1. This test report cannot be reproduced except in full, without written approval of the laboratory. This is not applicable when part report is given due to failure of the machine or test in progress.
2. Sampling done by the party. The test samples are submitted by the client. The sample descriptions provided in the test report are based on declaration by the party.
3. This report pertains to the submitted samples only.

-----End of Test Report-----

TESTED BY YK

ASST./DY./JT. DIRECTOR

HEAD
LABORATORIES DIVISION

This report is for Private use only Not to be used for Publicity or Litigation

Testing laboratories of Mumbai are certified by ISO 9001: 2015, NABL, BIS, Directorate General of Shipping and Directorate General of Civil Aviation, Govt. of India for specified tests.

Head Office: Plot E-2, Road No. 8, MIDC, Area, Andheri (East), Mumbai 400093.

Tel: +91-22-2821 9803 / 6751 / 9469, 28391506, 28329623, 28254631, Fax: +91-22-28328178 / 28375302 Email : rdiip@iip-in.com, Website: www.iip-in.com



भारतीय पैकेजिंग संस्थान
Indian Institute of Packaging

An autonomous body under the Ministry of Commerce & Industry, Govt. of India

LABORATORY TEST REPORT

Form / Format No : 32

Page 1 of 1

Issued To : A-1 AIR PROOF Gala No.32, Manish Ind. No. 5, Navgar Road, Vasai Road (E), Thane - 401 210, Maharashtra. Kind Attn : --	Test Report No	100/02-1718/7787
	Date	19 Mar 2018
	Date of Start of Test	07 Feb 2018
	Date of Completion of Test	19 Mar 2018
	Customer Ref.No	Covering Letter
	Ref. Date	05 Feb 2018
	Sampling Plan	Sampling done by the party
Sample Description : One set of sample said to be food container with cap.		

Test Results

Sr No.	Test	Unit	Results Obtained	Tested as per
1	Overall Migration (Extraction value) with distilled water at 40°C for 10 days	mg/L	4.00 (No colour Migration was observed.)	IS 9845 - 1998 RA 2010
2	Overall Migration (Extraction value) with 3% Acetic Acid at 40°C for 10 days	mg/L	10.66 (No colour Migration was observed.)	IS 9845 - 1998 RA 2010
3	Overall Migration (Extraction value) with n-heptane at 38°C for 30 min	mg/L	5.73 (No colour Migration was observed.)	IS 9845 - 1998 RA 2010

General Remarks

1. This test report cannot be reproduced except in full, without written approval of the laboratory. This is not applicable when part report is given due to failure of the machine or test in progress.
2. Sampling done by the party. The test samples are submitted by the client. The sample descriptions provided in the test report are based on declaration by the party.
3. This report pertains to the submitted samples only.

End of Test Report

TESTED BY SRD

ASST./DY./JT. DIRECTOR

DR. S. K. Chattopadhyay
Prof. & Additional Director
LABORATORIES DIVISION

This report is for Private use only. Not to be used for Publicity or Litigation

Testing laboratories of Mumbai are certified by ISO 9001: 2015, NABL, BIS, Directorate General of Shipping and Directorate General of Civil Aviation. Govt. of India for specified tests.

Scanned with CamScanner